



# Yueyang Expreview Trading Co. Ltd

Address: 34th, Yunxin avenue, Chenglingji New Port District, Yueyang, Hunan Province.  
Tel: +86 198-0740-2881 Whatsapp: +86 152-7301-2808 E-mail: johnnyfang@bpa-epoxy.com

双酚A型液体环氧树脂产品技术指标: Bisphenol A liquid epoxy resin specifications

序号 No.	牌号 Brand	环氧当量 Epoxy equivalent (g/mol)	可水解氯 Hydrolysable chlorine, wt% ≤	无机氯 Inorganic chlorine, wt %≤	软化点 Softening Point (°C)	粘度 Viscosity (mPa. s 25°C)	挥发份 Volatile , wt%≤	色度		主要用途 Application
								铂-钴色号 Platinum-cobalt ≤	加德纳色号 Gardner≤	
1	CYD-127	180-190	0.1	-	-	8000-11000	0.2	60	-	电气H级、绝缘漆层压材料等 Electrical, Insulating Paint, Laminates, etc.
2	CYD-127E	180-186	0.035	-	-	10000-13000	0.2	60	-	电工 Electrician
3	CYD-128	184-194	0.1	-	-	11000-14000	0.2	60	-	基础树脂多种用途 Base resin for various purposes
4	CYD-128D	186-190	0.035	-	-	12000-16000	0.2	60	-	胶黏剂 Adhesive
5	CYD-128E	184-194	0.02-0.04	-	-	11000-14000	0.2	60	-	电泳漆等特殊用途 Electrophoretic paint and other special purposes
6	CYD-128M	186-190	0.15	-	-	12500-14500	0.05	20	-	美缝剂 Beauty agent
7	CYD-128Y	187-193	0.1	-	-	12000-15000	0.2	40	-	光固化涂料 Light Curing Coatings
8	CYD-128YL	185-189	0.03	-	-	10000-16000	0.05	20	-	光固化 Light Curing
9	CYD-128S	205-225	1.8-2.4	-	-	19000-24000	0.2	60	-	多种用途 Multiple uses
10	CYD-128F	186-190	0.05	-	-	12500-14000	0.2	40	-	地坪涂料 Floor coating
11	CYD-188	187-189	0.028	-	-	12500-14300	0.2	30	-	汽车涂料专用料 Special materials for automotive coatings
12	CYD-134	230-270	0.1	-	21-27	-	0.3	-	1	涂料浇注 Paint pouring
13	CYD-115	180-194	0.1	-	-	700-1100	10.0	-	1	无溶剂涂料 Solvent Free Coatings
14	CYD-115C	195-215	1.7-2.0	-	-	800-1600	12.0	-	1	无溶剂涂料 Solvent Free Coatings
15	E-44	210-240	0.3	0.018	14-22	-	0.6	-	1	粘合、浇铸、密封、浸渍、层压 Bonding, casting, sealing, impregnating, laminating
16	E-44(II)	215-240	0.3	0.018	15-23	-	0.6	-	1	粘合、浇铸、密封、浸渍、层压 Bonding, casting, sealing, impregnating, laminating
17	E-42	230-280	0.3	0.01	21-27	-	0.5	-	1	粘合、浇铸、密封、浸渍、层压 Bonding, casting, sealing, impregnating, laminating
18	E-39D	240-256	0.4	0.002	24-29	-	-	-	1	电器、互感器 Electrical appliances, transformers

注1: 密度、钠离子含量、总氯含量指标由供需双方商定 / Note 1: Density, sodium ion content and total chlorine content shall be negotiated by both parties.

注2: E-39D凝胶时间由供需双方商定 / Note 2: E-39D gel time is negotiated by both parties

注3: 环氧当量1g/mol=1g/eq / Note 3: Epoxy equivalent 1g/mol=1g/eq