



Yueyang Expreview Trading Co. Ltd

Address: 34th, Yunxin avenue, Chenglingji New Port District, Yueyang, Hunan Province.
Tel: +86 198-0740-2881 Whatsapp: +86 152-7301-2808 E-mail: johnnyfang@bpa-epoxy.com

水性环氧树脂产品技术指标: Waterborne epoxy resin specifications

序号 No.	牌号 Brand	环氧当量 Epoxy equivalent (g/mol)	粘度 Viscosity (mPa. s 25℃)	固含量, % (质量分数) Solid content% (Mass fraction)	离心稳定性 Centrifugal stability 3000rpm, 20min	主要用途 Application
1	CYDW-102W50	400-800	≤800	50±2	不分层	玻璃纤维和碳纤维浸润定型剂 Glass fiber and carbon fiber impregnation and
2	CYDW-112W50	1200-1850	500-3000	50±2	不分层	防腐涂料、地坪涂料、混凝土改性等 Anti-corrosion coatings, floor coatings, concrete
3	CYDW-113W50	1200-1850	2000-8000	50±2	不分层	防腐涂料、地坪涂料、混凝土改性等 Anti-corrosion coatings, floor coatings, concrete
4	CYDW-100	190-210	500-1500	-	-	环氧底漆、环氧地坪涂料、胶粘剂、环氧砂浆、混凝土改性等 Epoxy primer, epoxy floor coating, adhesive, epoxy mortar, concrete modification, etc.
5	CYDW-100P	195-215	500-2000	-	-	
6	CYDW-100A	175-205	3000-4500	-	-	
7	CYDW-136	180-200	6000-7000	-	-	透水砖、透水路面铺装 Permeable brick, permeable pavement
8	CYDW-137	220-240	750-950	-	-	水性勾缝剂 water-based grout
9	CYDW-125	200-230	8000-12000	-	-	水性勾缝剂 water-based grout
10	YR-909N	210-240	11000-15000	-	-	水性勾缝剂 water-based grout

注3: 环氧当量1g/mol=1g/eq/Note 3: Epoxy equivalent 1g/mol=1g/eq

序号 No.	牌号 Brand	胺值 Amine value (mgKOH/g)	粘度 Viscosity(mPa. s 25℃)	主要用途 Application
1	CYDHD-280	260-320	280-400	胶粘剂、环氧砂浆、混凝土改性、防腐涂料等 Adhesives, epoxy mortar, concrete modification, anti-corrosion coatings, etc.
2	CYDHD-220	160-200	1000-3000	环氧地坪涂料、胶粘剂、环氧砂浆、混凝土改性等 Epoxy floor coatings, adhesives, epoxy mortar, concrete modification, etc.
3	CYDHD-200	220-280	1200-3000	
4	CYDHD-236	1000-1350	30-150	水性勾缝剂、透水砖、透水路面铺装等 Water-based grout, permeable brick, permeable pavement, etc.